

**Deutsche Magnetwerke GmbH** 

Date of issue: 09/2016

## Datasheet AINiCo 400K

Anisotropic cast material

## Magnetic Specifications

AlNiCo 26/6 according to IEC Standard		Minimum Values		Typical Values	
(DIN IEC 60404-8-1, chart 9)					
Br	Remanence	9.000 G	900 mT	10.500 G	1.050 mT
(BH) <sub>max</sub>	Max. Energy product	3,27 MGOe	26,0 kJ/m <sup>3</sup>	3,8 MGOe	30,2 kJ/m <sup>3</sup>
H <sub>cB</sub>	Coercivity force	704 Oe	56,1 kA/m	785 Oe	62,5 kA/m
H <sub>cJ</sub>	Intrinsic coercivity force	729 Oe	58,0 kA/m	800 Oe	63,7 kA/m
TK(B <sub>R</sub> )	Temperature coefficient of induction			-0,02 %/K	Within a range of 25 °C – 200°C
$\mu_{rec}$	Relative permanent permeability			3,0-5,0	
Hs	Field strength of saturation			3000 Oe	240 kA/m

Specific for anisotropic materials is the fixed magnetic direction. Magnets must be magnetized through this direction to reach the magnetic values in accordance to the use of them. Especially for block- and ring shaped magnets it is necessary to declare the specific magnetic direction at ordering. Cylinder shaped dimensions have the magnetic direction through the axis by default.


## Physically and chemical specifications

8Al; 15Ni; 25Co; 3Cu; 1Ti; 1Nb; bal. Fe		
$7,3 \text{ g/cm}^3$		
860 °C		
450 °C		
11,3 x 10 <sup>-6</sup> /°C		
0,5 μΩm		
ca. 500 - 600		
1200 - 2200 N/mm <sup>2</sup>		

The resistance to chemicals is similar to high alloy steels but inconsistent in inorganic acids, salt water or in strong alkaline solutions. The material will not be affected in organic solvents, alcohols, oils or gasoline.

It is not toxic and its environmental behavior is neutral. Persons who are sensitive to nickel can have side effects, same as for other nickelous materials. Please beware direct contact to foodstuffs and do not use it in toys. For these kinds of use it is advisable to cover the magnets with plastic or a food safe finish.

These magnets are very hard and brittle, outbreaking grains are possible and the material can be machined with abrasive proceedings (e.g. surface and cylindrical grinding)



Internet: <u>www.guss-magnete.de</u> Mail: info@guss-magnete.de